

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C09D 4/00, C08F 216/00, 222/10, C08G 59/30, 59/32</b>		<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/39390</b>
			<b>(43) International Publication Date:</b> 11 September 1998 (11.09.98)
<b>(21) International Application Number:</b> PCT/US98/04845 <b>(22) International Filing Date:</b> 6 March 1998 (06.03.98) <b>(30) Priority Data:</b> 08/813,559                      7 March 1997 (07.03.97)                      US <b>(71) Applicant:</b> THE WALMAN OPTICAL COMPANY [US/US]; 801 12th Avenue North, Minneapolis, MN 55411 (US). <b>(72) Inventor:</b> TREADWAY, Gerald, D.; 6222 Lichau Road, Penn Grove, CA 94951 (US). <b>(74) Agents:</b> HALLER, James, R. et al.; Fredrikson & Byron, P.A., 1100 International Centre, 900 2nd Avenue South, Minneapolis, MN 55402-3397 (US).			<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> UV-CURABLE ABRASION-RESISTANT COATING COMPOSITION			
<b>(57) Abstract</b>  A coating composition for forming a transparent, abrasion-resistant coating upon eyeglass lenses or other transparent substrates, the composition comprising a binder component and a curing agent component and being substantially free of volatiles. The binder component comprises the hydrolysis product of an epoxy-functional alkoxy silane, a polyglycidyl ether, and an acrylic monomer having an acrylic functionality of not more than two. The curing agent component comprises a cationic photoinitiator and a free radical photoinitiator.			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

UV-Curable Abrasion-Resistant Coating Composition.Field of the Invention

The invention relates to the field of transparent coatings for transparent objects such as eyeglass lenses, windows and the like, and refers particularly to a coating having  
5 an index of refraction essentially equal to that of the substrate that is coated.

Background of the Invention

Transparent plastic materials such as eyeglass lenses, television screen face plates and the protective coatings on photographic prints often are quite soft and are subject to becoming dull and hazy due to scratching and abrasion during use.  
10 Polycarbonate eyeglass lenses, for example, are strong and shatter resistant but also are relatively soft and susceptible to scratching. Television screen face plates similarly are made of flexible, shatter resistant plastic materials such as polycarbonate and poly (methylethacrylate), and these also can be scratched or abraded.

Various coatings have been proposed for eyeglasses and other transparent plastic  
15 materials to reduce their propensity to become scratched and abraded. One such composition is shown in U.S. Patent 4,378,250 (Treadway, *et al.*) granted March 29, 1983. Other coatings are shown in U.S. Patents 5,367,019 (Sawara), 4,855,180 (Kawamura), 4,895,767 (Mori *et al.*) and 4,719,146 (Hohage *et al.*) Besides being abrasion resistant, coatings for eyeglass lenses should also be capable of being tinted by treatment with a dye  
20 which becomes incorporated in the coating. As a general observation, the tintability of a coating tends to decrease as its hardness and scratch resistance increases, and vice-versa.

Harasta, *et al.* U.S. Patent 4,426,431 discusses a coating composition referred to as a "hybrid " system because it employs a solution, in a solvent such as propylene carbonate, an epoxy compound and a cationic initiator for it, and an acrylic compound and a free  
25 radical initiator for it. In general, coating compositions suitable for use in forming protective transparent coatings on eyeglass lenses and the like are provided in solution in a volatile solvent, the solvent serving as a low viscosity vehicle to enable the coating composition to be uniformly spread upon a surface and to accept dye treatments. The solvents that are employed are for the most part organic, and must be used and disposed of  
30 carefully.

Perkins *et al.* U.S. Patent 5,221,560 describes a coating composition containing a polyfunctional, polymerizable non-acrylate functional ether, a radiation-sensitive initiator,

and colloidal silica in an amount providing at least 25% by weight of the total solids of the composition, the silica being reacted with a small amount of a hydrolyzed acryloxy-functional or glycidoxy-functional silane.

It would be desirable to provide a coating composition that on the one hand is  
5 capable of forming coatings having both excellent abrasion resistance and dye acceptance.


#### Summary of the Invention

The present invention utilizes a coating composition that utilizes that accepts dye well, that provides exceptional abrasion-resistance, and that is substantially free of  
volatiles. The composition includes at least 10% by weight, solids basis, of an at least  
10 partially hydrolyzed epoxy-functional alkoxysilane. Included also in the composition is a polymerizable ether, desirably cationically polymerizable, selected from the group consisting of glycidyl ethers, allyl ethers and vinyl ethers, and an ethylenically unsaturated monomer component, desirably an acrylic monomer component that preferably includes a monomer having an acrylic functionality of not more than two. A cationic photoinitiator  
15 is employed to affect polymerization of the epoxy-functional components, and a free radical initiator is employed to initiate polymerization of the ethylenically unsaturated coating components, that is, the acrylic-functional component. The polymerizable ethers improve tintability of the resulting coating, and use of the acrylic monomer results in excellent adhesion to polycarbonate substrates.

20 Hydrolysis of the alkoxysilane may but need not be complete, and preferably, the alkoxysilane is reacted with a stoichiometrically sufficient quantity of water to hydrolyze at least 50% of the alkoxy groups and most preferably from about 60% to about 70% of the alkoxy groups. In a preferred embodiment, the coating composition is substantially free of volatile solvents and also preferably is free of silica.

#### 25 Description of the Preferred Embodiments

The epoxy functional alkoxy silane precursor of the at least partially hydrolyzed polymerizable ingredient is preferably an epoxyalkylalkoxysilane of the following structure:



30 wherein  $R_1$  is a  $C_1 - C_{14}$  alkylene group,  $R_2$  and  $R_3$  independently are  $C_1 - C_4$  alkyl groups and  $Q$  is a glycidoxy or epoxycyclohexyl group, and  $m$  is 0 or 1. The alkoxy groups are at least partially hydrolyzed to form silanol groups with the release of the  $R_3OH$  alcohol, and

some condensation of the silanol groups occurs. Epoxy reactivity is preserved, however. Many epoxy-functional alkoxysilanes are suitable as hydrolysis precursors, including glycidoxymethyl-trimethoxysilane, glycidoxymethyltriethoxysilane, glycidoxymethyl-tripropoxysilane, glycidoxymethyl-tributoxysilane, b -glycidoxyethyltrimethoxysilane, b -glycidoxyethyltriethoxysilane, b -glycidoxyethyl-tripropoxysilane, b -glycidoxyethyl-tributoxysilane, b -glycidoxyethyltrimethoxysilane, a -glycidoxyethyl-triethoxysilane, a -glycidoxyethyl-tripropoxysilane, a -glycidoxyethyltributoxysilane, g -glycidoxypropyl-trimethoxysilane, g -glycidoxypropyl-triethoxysilane, g -glycidoxypropyl-tripropoxysilane, g -glycidoxypropyltributoxysilane, b -glycidoxypropyl-trimethoxysilane, b -glycidoxypropyl-triethoxysilane, b -glycidoxypropyl-tripropoxysilane, b -glycidoxypropyltributoxysilane, a -glycidoxypropyl-trimethoxysilane, a -glycidoxypropyl-triethoxysilane, a -glycidoxypropyl-tripropoxysilane, a -glycidoxypropyltributoxysilane, g -glycidoxybutyl-trimethoxysilane, d -glycidoxybutyl-triethoxysilane, d -glycidoxybutyl-tripropoxysilane, d -glycidoxybutyl-tributoxysilane, d -glycidoxybutyl-trimethoxysilane, g -glycidoxybutyl-triethoxysilane, g -glycidoxybutyl-tripropoxysilane, g -propoxybutyl-tributoxysilane, d -glycidoxybutyl-trimethoxysilane, d -glycidoxybutyl-triethoxysilane, d -glycidoxybutyl-tripropoxysilane, a -glycidoxybutyl-trimethoxysilane, a -glycidoxybutyl-triethoxysilane, a -glycidoxybutyl-tributoxysilane, (3,4-epoxycyclohexyl)-methyl-trimethoxysilane, (3,4-epoxycyclohexyl)methyl-triethoxysilane, (3,4-epoxycyclohexyl)methyl-tripropoxysilane, (3,4-epoxycyclohexyl)-methyl-tributoxysilane, (3,4-epoxycyclohexyl)ethyl-trimethoxysilane, (3,4-epoxycyclohexyl)ethyl-triethoxysilane, (3,4-epoxycyclohexyl)ethyl-tripropoxysilane, (3,4-epoxycyclohexyl)-ethyl-tributoxysilane, (3,4-epoxycyclohexyl)propyl-trimethoxysilane, (3,4-epoxycyclohexyl)propyl-triethoxysilane, (3,4-epoxycyclohexyl)propyl-tripropoxysilane, (3,4-epoxycyclohexyl)propyl-tributoxysilane, (3,4-epoxycyclohexyl)butyl-trimethoxysilane, (3,4-epoxycyclohexyl) butyl-triethoxysilane, (3,4-epoxycyclohexyl)-butyl-tripropoxysilane, and (3,4-epoxycyclohexyl)butyl-tributoxysilane.

A particularly preferred epoxyalkylalkoxysilane is  $\gamma$  -glycidoxypropyl trimethoxy silane due to its wide commercial availability.

Hydrolysis of the epoxy-functional alkoxysilane precursor may occur in an acidic environment, and reference is made to U.S. patent 4,378,250, the teachings of which are

incorporated herein by reference. Hydrolysis of the alkoxy groups liberates the associated alcohol to form silanol groups; these, in turn, are relatively unstable and tend to condense spontaneously. Preferably, the alkoxy silane is reacted with a stoichiometrically sufficient quantity of water to hydrolyze at least 50% of the alkoxy groups and most preferably from  
5 about 60% to about 70% of the alkoxy groups. For the hydrolysis of an epoxy-functional trialkoxy silane, good results have been obtained by reacting the silane with a stoichiometrically sufficient quantity of water to hydrolyze two-thirds of the alkoxy groups.

The at least partially hydrolyzed epoxy-functional silane is present in the coating compositions of the invention at a weight concentration (solids basis) of 10% to 75 %, and  
10 preferably 20% to 50%.

Useful cationic initiators for the purposes of this invention include the aromatic onium salts, including salts of Group Va elements, such as phosphonium salts, e.g., triphenyl phenacylphosphonium hexafluorophosphate, salts of Group VIa elements, such as sulfonium salts, e.g., triphenylsulfonium tetrafluoroborate, triphenylsulfonium  
15 hexafluorophosphate and triphenylsulfonium hexafluoroantimonate, and salts of Group VIIa elements, such as iodonium salts, e.g., diphenyliodonium chloride. The aromatic onium salts and their use as cationic initiators in the polymerization of epoxy compounds are described in detail in U.S. Pat. No. 4,058,401, "Photocurable Compositions Containing Group VIA Aromatic Onium Salts," by J. V. Crivello issued Nov. 15, 1977; U.S. Pat. No.  
20 4,069,055, "Photocurable Epoxy Compositions Containing Group VA Onium Salts," by J. V. Crivello issued Jan. 17, 1978, U.S. Pat. No. 4,101,513, "Catalyst For Condensation Of Hydrolyzable Silanes And Storage Stable Compositions Thereof," by F. J. Fox et al. issued July 18, 1978; and U.S. Pat. No. 4,161,478, "Photoinitiators," by J. V. Crivello issued July 17, 1979, the disclosures of which are incorporated herein by reference. Other  
25 cationic initiators can also be used in addition to those referred to above; for example, the phenyldiazonium hexafluorophosphates containing alkoxy or benzyloxy radicals as substituents on the phenyl radical as described in U.S. Pat. No. 4,000,115, "Photopolymerization Of Epoxides," by Sanford S. Jacobs issued Dec. 28, 1976, the disclosure of which is incorporated herein by reference. Preferred cationic initiators for  
30 use in the compositions of this invention are the salts of Group VIa elements and especially the sulfonium salts. Particular cationic catalysts include diphenyl iodonium salts of tetrafluoro borate, hexafluoro phosphate, hexafluoro arsenate, and hexafluoro

antimonate; and triphenyl sulfonium salts of tetrafluoroborate, hexafluoro phosphate, hexafluoro arsenate, and hexafluoro antimonate.

The polymerizable ether component imparts tintability, and is selected from the group consisting of glycidyl ethers, allyl ethers and vinyl ethers. The polymerizable ethers may be monofunctional or polyfunctional, preferably polyfunctional, and desirably are cationically polymerizably. Mixtures of the polymerizable ethers may be used, particularly mixtures of glycidyl ethers and vinyl ethers. These ethers preferably are non-acrylate functional.

Glycidyl ethers useful in the invention include triglycidyl ether,  $\gamma$ -glycidoxypropyl trimethoxy silane, triglycidyl ether, 1,4-butanediol diglycidyl ether, Bisphenol A diglycidyl ether, the  $C_8$ - $C_{14}$  alkyl glycidyl ethers, butyl glycidyl ether, cresyl glycidyl ether, phenyl glycidyl ether, nonylphenyl glycidyl ether, p-tert-butylphenyl glycidyl ether, 1,4-butanediol diglycidyl ether, neopentyl glycol diglycidyl ether, resorcinol diglycidyl ether, polyglycidyl ethers of aliphatic polyols, cyclohexane dimethanol diglycidyl ether, 2-ethylhexyl glycidyl ether, polyglycol diepoxide, polyglycidyl ether of castor oil, trimethylolethane triglycidyl ether, trimethylolpropane triglycidyl ether, dibromoneopentyl glycol diglycidyl ether, and 3,4-epoxycyclohexyl methyl-3,4-epoxycyclohexane carboxylate. Glycidyl ethers, if used alone as the polymerizable ether, are present preferably in a weight concentration (solids basis) of from about 10% to about 50%.

Allyl ethers include 1,1,2,2-tetraallyloxyethane, triallylcyanurate, polyallylglycidyl ether, and allylglycidyl ether. Allyl ethers, if used alone as the polymerizable ether, preferably are employed at a weight concentration (solids basis) of up to about 10%.

Vinyl ethers include triethylene glycol divinyl ether, diethylene glycol divinyl ether, tetraethylene glycol divinyl ether, dipropylene glycol divinyl ether, tripropylene glycol divinyl ether, 1,4-divinyloxybutane, and, as a preferred ether, cyclohexane dimethanol divinyl ether. If used alone as the polymerizable ether, a vinyl ether preferably is employed at a weight concentration (solids basis) not greater than about 15%, and most preferably in the range of about 5% to about 10%.

As noted above, the polymerizable ether ingredient may consist of a mixture of two or more ethers, the relative amounts of which are chosen so as to provide the cured coating with good tintability while maintaining acceptable adhesion to substrates. Employing too

much of the polymerizable ether may tend to adversely affect adhesion of the coating to substrates, particularly polycarbonate substrates.

Of the ethylenically unsaturated monomers, vinyl acetate contributes to good adhesion to polycarbonate substrates. However, acrylic-functional monomers and oligomers are preferred. Useful acrylic compounds for improving adhesion to polycarbonate substrates include both mono and di-functional monomers, but other or additional polyfunctional acrylic monomers may also be included. Examples of monofunctional acrylic monomers include acrylic and methacrylic esters such as ethyl acrylate, butyl acrylate, 2-hydroxypropyl acrylate, cyclohexyl acrylate, 2-ethylhexyl acrylate, methyl methacrylate, ethyl methacrylate, and the like. Examples of polyfunctional acrylic monomers, including both difunctional and tri and tetrafunctional monomers, include neopentylglycol diacrylate, pentaerythritol triacrylate, 1,6-hexanediol diacrylate, trimethylolpropane triacrylate, tetraethylene glycol diacrylate, 1,3-butylene glycol diacrylate, trimethylolpropane trimethacrylate, 1,3-butylene glycol dimethacrylate, ethylene glycol dimethacrylate, pentaerythritol tetraacrylate, tetraethylene glycol dimethacrylate, 1,6-hexanediol dimethacrylate, ethylene glycol diacrylate, diethylene glycol diacrylate, glycerol diacrylate, glycerol triacrylate, 1,3-propanediol diacrylate, 1,3-propanediol dimethacrylate, 1,2,4-butanetriol trimethacrylate, 1,4-cyclohexanediol diacrylate, 1,4-cyclohexanediol dimethacrylate, pentaerythritol diacrylate, 1,5-pentanediol dimethacrylate, and the like. The acrylic-functional monomers and oligomers preferably are employed at a weight concentration of from about 10% to about 50% on a solids basis

Although photoactivated free-radical initiator are preferred, thermally activated free radical initiators may also be used. Useful photoinitiators for this purpose are the haloalkylated aromatic ketones, chloromethylbenzophenones, certain benzoin ethers, certain acetophenone derivatives such as diethoxyacetophenone and 2-hydroxy-2-methyl-1-phenylpropan-1-one. A preferred class of free-radical photoinitiators is the benzil ketals, which produce rapid cures. A preferred photoinitiator is  $\alpha,\alpha$ -dimethoxy- $\alpha$ -phenyl acetophenone (Iragacure™ 651, Ciba-Geigy, disclosed in U.S. Pat. Nos. 3,715,293 and 3,801,329). The most preferred photoinitiator, in accordance with this invention, is 2-hydroxy-2-methyl-1-phenylpropane-1-one (Darocure™ 1173, Ciba-Geigy Corporation). Specific examples of photoinitiators include ethyl benzoin ether, isopropyl benzoin ether, dimethoxyphenyl acetophenone, diethoxy acetophenone, and benzophenone.



The invention may be better understood by reference to the following non-limiting examples. Cured coatings were subjected to several tests, outlined as follows:

Scratch Resistance:

The coated substrate is supported in a jig and a pad of 0000 grade steel wool  
5 attached to a support with a weight of 5 p.s.i. is rubbed across the surface automatically for  
50 strokes, one stroke being forward and back. The change in haze is measured  
spectrophotometrically, and is reported as the percentage loss in transmissivity.

Adhesion:

Adhesion may be measured using the procedures of ASTM 3359. This test, in  
10 brief, provides for scoring of the cured coating with a sharp instrument in a cross-hatched  
fashion to leave diamond-shaped patches, followed by an attempt to lift the diamond-  
shaped patches from the substrate through the use of a pressure sensitive adhesive tape that  
is applied to the cross hatched surface and then pulled away. The degree to which the  
cross-hatched portions of the coating remain adhered to the substrate provides a measure  
15 of adhesion to that substrate, and is reported as the percentage of diamond-shapes that  
remain adhered to the substrate.

Tintability:

A coated and cured sample is immersed in BPI Black Dye (Brain Power Inc.) at  
98-102°C for 15 minutes and then rinsed with water and dried. Transmissivity is  
20 measured spectrophotometrically, and tintability is reported as percentage transmissivity.

Example 1

A master batch of the partial hydrolysis product of  $\gamma$  glycidoxy propyl trimethoxy silane is  
prepared as follows:

	$\gamma$ -glycidoxy propyl trimethoxy silane	868.3 gm
25	Water.	131.2 gm
	Conc. HCL	0.5 gm

The above ingredients are stirred together in a flask equipped with a condenser for 12-16  
hours, during which substantially all of the volatiles are removed using a rotary  
evaporator. Sufficient water is used in this example to theoretically hydrolyze 2 of the 3  
30 alkoxy groups.

## Example 2

	Master batch of Example 1.	25.35 gm
	Butane diol diacrylate	23.47 gm
	Trimethylol Propane Triglycidyl Ether	37.55 gm
5	Mixed Triarylsulfonium Hexafluoroantimonate Salts	9.39 gm
	50% in Propylene Carbonate (UVI 6974, Union Carbide)	
	2-hydroxy-2-methyl-1-phenylpropane-1-one	2.35 gm
	(Darocure™ 1173, Ciba-Geigy Corporation)	
	Acrylated Silicone Flow Control Agent	1.89 gm
10	(Ebecryl™ 1360, UCB Radcure Co.)	

The material was spin coated on a polycarbonate substrate and cured using a 300 watt per inch mercury bulb. The cured film exhibited the following properties.

	Scratch Resistance	< 1% haze
	Adhesion after tint	100% (using 3M 600 tape)
15	Tintability	< 10 % transmission.

## Example 3

	Master batch of Example 1	26.38 gm
	Butane diol diacrylate	34.2 gm
	Trimethylol Propane Triglycidyl Ether	19.54 gm
20	Trimethylol Propane Triacrylate	9.77
	UVI 6974	4.88
	Darocure 1173	3.25
	Ebecryl 1360	1.98

The coating composition was coated on a polycarbonate substrate and cured as in Example

## 25 1. Testing results were as follows:

	Scratch Resistance	< 0.5% Haze
	Adhesion after tint	100 %
	Tintability	< 16.0 % transmissivity

## Example 4

30	Master batch of Ex. 1	26.87
	Butane Diol Diacrylate	24.88

	Trimethylol Propane Triglycidyl Ether	29.85
	Trimethylol Propane Triacrylate	9.95
	UVI 6974	2.99
	Darocure 1173	3.48
5	Ebecryl 1360	1.99
	Total	100.0

The coating composition was coated and tested as in Example 1, yielding the following test results:

	Scratch resistance	< 0.5% Haze
10	Adhesion after tint	100%
	Tintability	< 15.0% Transmission

#### Example 5

	Master batch of Example 1	22.83
	Butane Diol Diacrylate	27.40
15	Dipentaerythritol Hydroxy Pentacrylate	22.83
	Cyclohexane 1,4, Dimethylol Divinyl Ether	18.26
	UVI 6974	2.28
20	Darocure 1173	4.56
	Acrylated Silicone Flow Control	1.84
	Agent (BYK™ 371, BYK Co.)	
	Total	100.0

The composition was coated and cured as in Example 1, and the following test results were obtained:

	Scratch Resistance	< 1.0% Haze
	Adhesion after tint	100k%
	Tintability	< 6.0% Transmission

#### Example 5

30	Master batch of Example 1	27.40
	Butane Diol Diacrylate	27.40

	Dipentaerythritol Hydroxy Pentacrylate	22.83
	Cyclohexane 1,4, Dimethylol Divinyl Ether	13.70
	UVI 6974	2.28
	Darocure 1173	4.57
5	BYK 371	1.83
	Total	100.0

The composition was coated on Polycarbonate as in Example 1. The following test results were obtained:

	Scratch Resistance	< 0.8% Haze
10	Adhesion after tint	100%
	Tintability	< 6.0% Transmission

While a preferred embodiment of the present invention has been described, it should be understood that various changes, adaptations and modifications may be made therein without departing from the spirit of the invention and the scope of the appended

15 claims.

What is claimed is:

1. A coating composition for forming a transparent, abrasion-resistant coating upon a substrate, the composition comprising a binder component and a curing agent component, the binder component comprising at least 10% by weight, solids basis, of the hydrolysis product of an epoxy-functional alkoxy silane, a polymerizable ether selected from the group consisting of glycidyl ethers, allyl ethers and vinyl ethers, and an ethylenically unsaturated monomer, the curing agent component comprising a cationic initiator and a free radical initiator.
2. The coating composition of claim 1 wherein said ethylenically unsaturated monomer comprises an acrylic monomer.
3. The coating composition of claim 1 wherein said ethylenically unsaturated monomer comprises vinyl acetate.
2. The coating composition of claim 1 wherein said hydrolysis product comprises the product of the partial hydrolysis of a glycidoxymethylalkoxy silane.
3. The coating composition of claim 1 wherein said hydrolysis product is present in an amount ranging from 10 to 75 weight percent of the coating composition.
4. The coating composition of claim 1 wherein said hydrolysis product is the reaction product of  $\gamma$ -glycidoxypentyl trimethoxysilane and a stoichiometrically sufficient quantity of water to hydrolyze greater than 50% of the methoxy groups
5. The coating composition of any one of claims 1 - 4, wherein the coating composition is substantially free of volatiles or silica or both.

# INTERNATIONAL SEARCH REPORT

national Application No

PCT/US 98/04845

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09D4/00 C08F216/00 C08F222/10 C08G59/30 C08G59/32

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 221 560 A (PERKINS WILLIAM C ET AL) 22 June 1993 cited in the application see column 4, line 45 - column 5, line 55 see column 6, line 66 - column 7, line 17 see column 8, line 24 - line 58 see example 3 see claims 1-12, 17, 18, 21 ---	1-7
Y	DATABASE WPI Derwent Publications Ltd., London, GB; AN 82-58524e XP002069615 "Electron beam hardenable compositions" & JP 57 092 023 A (DAINIPPON PRINTING CO. LTD.) see abstract -----	1-7

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance  
 "E" earlier document but published on or after the international filing date  
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  
 "O" document referring to an oral disclosure, use, exhibition or other means  
 "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone  
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.  
 "&" document member of the same patent family

Date of the actual completion of the international search

26 June 1998

Date of mailing of the international search report

07/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

Bettels, B

# INTERNATIONAL SEARCH REPORT

Information on patent family members

national Application No

PCT/US 98/04845

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5221560 A	22-06-1993	US 5296295 A	22-03-1994
		AU 640912 B	09-09-1993
		AU 4912690 A	23-08-1990
		CA 2008020 A	17-08-1990
		CN 1046545 A,B	31-10-1990
		DE 69007826 D	11-05-1994
		DE 69007826 T	11-08-1994
		EP 0383074 A	22-08-1990
		JP 2269777 A	05-11-1990
		JP 2719021 B	25-02-1998